

Produktinformation

Hans Jiricek GmbH · Am Roten Kreuz 8 · D-78187 Geisingen / Donau
Phone +49 (0) 77 04 / 92 92 0 · Fax +49 (0) 77 04 / 92 92 30 · www.jiricek.de



Thermokraftpapier 0,065

Artikel Gruppe 150

<u>Property</u>	<u>Unit</u>	<u>Testmethod</u>	<u>Minimum</u>	<u>Nominal</u>	<u>Maximum</u>
Grammage	g / m ²	ISO 536	49,5	52	54,5
Bulking thickness / 5 sheet	µm	ISO 534	59	65	71
Apparent bulk density	kg / m ³	ISO 534	750	800	850
Air resistance (gurley)	sec / 100cc	ISO 5636-5	128		256
Air permeability	µm / Pa*s	ISO 5636-5	0,5		1
Moisture content	%	ISO 287			8
Tensile index MD	Nm / g	ISO 1924-1	93		
Tensile index CD	Nm / g	ISO 1924-1	34		
Elongation MD	%	ISO 1924-2	2		
Elongation CD	%	ISO 1924-2	4		
Tear index MD	mN*m ² / g	ISO 1974	5		
Tear index CD	mN*m ² / g	ISO 1974	6		
Ash content	%	ISO 2144			1
Electrical strength	kV / mm	IEC 60554-2	7		
Conductivity in extraxt	mS / m	IEC 60554-2			10
pH in extract		IEC 60554-2	6		8