

Produktinformation

Hans Jiricek GmbH · Am Roten Kreuz 8 · D-78187 Geisingen / Donau
Phone +49 (0) 77 04 / 92 92 0 · Fax +49 (0) 77 04 / 92 92 30 · www.jiricek.de



Krepp-Papier HDC 0,080

Artikel Gruppe 156

Property	Unit	Testmethod	min	nom	max
Grammage	g/m ²	ISO 536		80,0	
Thickness 5 sheets	µm	ISO 534	75	80	83
Density 5 sheets	kg/m ³	ISO 534		1000	
Moisture content	%	ISO 287			6,0
Tensile strength MD	kN/m	ISO 1924	6,2	7,0	
Tensile strength CD	kN/m	ISO 1924	2,0		
Elongation MD	%	ISO 1924	15,0	20,0	
Elongation CD	%	ISO 1924	5,0		
Ash content	%	ISO 2144			0,5
pH		IEC 60554-2	6,0		8,0
Conductivity	mS/m	IEC 60554-2			10,0
Dielectric strength dry	kV/mm	IEC 60554-2	8,0		
Nitrogen Content	%	combustion	2,0		3,2
DP		IEC 60450	1200		